

[Baratè]

ALLUMINIO

[TOLLERANZE EN]

Barre tonde

Gruppo 1	Gruppo 2
EN AW-1050A	EN AW-2007
EN AW-6026	EN AW-2011
EN AW-6060	EN AW-7075
EN AW-6063	
EN AW-6082	




Tabella 1 – Gruppo Leghe 1

Dimensioni	Tolleranza
$\geq 8 \leq 18$	$\pm 0,22$
$\geq 18 \leq 25$	$\pm 0,25$
$\geq 25 \leq 40$	$\pm 0,30$
$\geq 40 \leq 50$	$\pm 0,35$
$\geq 50 \leq 65$	$\pm 0,40$
$\geq 65 \leq 80$	$\pm 0,50$
$\geq 80 \leq 100$	$\pm 0,60$
$\geq 100 \leq 120$	$\pm 0,70$

$\geq 120 \leq 150$	$\pm 0,85$
$\geq 150 \leq 180$	$\pm 1,0$
$\geq 180 \leq 220$	$\pm 1,1$
$\geq 220 \leq 260$	$\pm 1,3$
$\geq 260 \leq 300$	$\pm 1,6$
$\geq 300 \leq 350$	$\pm 2,0$

Tabella 2 – Gruppo Leghe 2

Dimensioni	Tolleranza
$\geq 8 \leq 18$	$\pm 0,30$
$\geq 18 \leq 25$	$\pm 0,30$
$\geq 25 \leq 40$	$\pm 0,35$
$\geq 40 \leq 50$	$\pm 0,40$
$\geq 50 \leq 65$	$\pm 0,50$
$\geq 65 \leq 80$	$\pm 0,70$
$\geq 80 \leq 100$	$\pm 0,90$
$\geq 100 \leq 120$	$\pm 1,0$
$\geq 120 \leq 150$	$\pm 1,2$
$\geq 150 \leq 180$	$\pm 1,4$
$\geq 180 \leq 220$	$\pm 1,7$
$\geq 220 \leq 260$	$\pm 2,0$
$\geq 260 \leq 300$	$\pm 2,5$
$\geq 300 \leq 350$	$\pm 3,0$

Tabella 3 – Rettilinearità

Diametro "d"		Rettilinearità	
		Ogni metro	Ogni 300 mm
>	≤	h1	h2
-	80	1	0,7
80	120	1	0,5
120	200	1	0,5
200	350	1	0,5

